

Crystalline Glaze Bases for Cone 10 Oxidation

TinFoil Δ8-10

Frit 3110	50
Zinc Ox.	25
Silica	18
Tin Ox.	2

Celestite Δ 9-10

Frit 3110	50
Zinc Ox.	25
Silica	15
Spodumene	5
Talc	4
Titanium Diox.	3

Norkin Δ 10

Lithium Carb.	0.18
Zinc Ox.	28.77
Frit 3110	43.59
Bentonite	2.18
Flint	15.28

Granite Δ 8-10

Frit 3110	48
Zinc Ox.	22
Silica	20
Titanium Diox.	10

Sawhill Δ 10

Titanium Diox.	7.8
Zinc Ox.	23.41
Spodumene	1.47
Frit 3110	45.85
Bentonite	1.47
EPK	1.46
Silica	18.54

Ilsley Δ 10

Frit 3110	44
Zinc	27
Flint	21
Titanium Diox.	8
Alumina Ox.	0.5
Molochite	0.5
Bentonite	0.2

Carol Sphar Δ 10

Frit 3134	15
Pemco Frit 283	40
Zinc Ox.	25
Flint	20

West Δ 10

Frit 3110	50
Zinc Ox	25
Flint	22
Titanium Diox.	5

Leon Bush Δ 10

Frit 3110	45.5
Zinc Ox.	27.5
Silica	20.0
EPK	1.35
Titanium Diox.	5.65